



# ARCOL<sup>®</sup> LG-650

## Polyether Polyol

**CAS No. 25791-96-2**

**Product Code: KLLG650**

### Description

Arcol LG-650 polyether polyol is a 260-molecular-weight polypropylene oxide-based triol. The terminal end-groups are predominantly secondary hydroxyls and have a relatively low reactivity. It is compatible with some polyether polyols and can be blended with other diols or triols to achieve desirable modifications of product properties.

Arcol LG-650 polyol is typically used in a broad range of urethane foam and other applications, including structural coatings, hard coatings, potting compounds, and thermal break. As with any product, the use of Arcol LG-650 polyol in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

### Product Specifications

Property	Value
Hydroxyl Number, mg KOH/g	640–660
Water, Wt. % (max)	0.07
Acid Number, mg KOH/g (max)	0.02
Color, Pt•Co (max)	100

### Typical Properties\*

Property	Value
Appearance	Clear, viscous liquid
Specific Gravity at 20°C	1.09
Viscosity at 25°C, cps	820
Flash Point, PMCC, °C	198
Bulk Density, lb/gal	9.11

### Storage

Arcol LG-650 polyol is slightly hygroscopic and may absorb water. Containers should be kept tightly closed and protected from contamination with moisture and foreign materials, which can adversely affect product quality.

This polyol can become quite viscous at low temperatures. For ease of handling, storage temperatures between ambient room temperature and 60°C (140°F) are recommended.

### Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Arcol LG-650 polyol. Before working with this product, you must read and become familiar with the available information on its hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets and product labels. Consult your Bayer MaterialScience representative or contact Bayer's Product Safety and Regulatory Affairs Department in Pittsburgh, Pa.

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Note: The information contained in this bulletin is current as of September 2003. Please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • [www.BayerMaterialScienceNAFTA.com](http://www.BayerMaterialScienceNAFTA.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications.

This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

---

Sales Offices

---

17320 Redhill Avenue, Suite 175, Irvine, CA 92614-5660 • 1-949-833-2351 • Fax: 1-949-752-1306  
1000 Route 9 North, Suite 103, Woodbridge, NJ 07095-1200 • 1-732-726-8988 • Fax: 1-732-726-1672  
2401 Walton Boulevard, Auburn Hills, MI 48326-1957 • Phone: 1-248-475-7700 • Fax: 1-248-475-7701

---

6160 9/03