



MONDUR[®] MRS 4

Polymeric MDI

CAS No. 9016-87-9

Product Code: G591

Product Information

Description

Mondur MRS 4 is a low-functionality polymeric diphenylmethane diisocyanate (PMDI) used in the formulation of coatings, elastomers, and molded flexible urethane foams. As with any product, use of Mondur MRS 4 isocyanate in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

Typical Properties*

Property	Value
Appearance	Dark brown liquid
NCO, Wt. %	32.2
Acidity, Wt. %	0.02
Viscosity** at 25°C, mPa·s	40
Specific Gravity at 25°C	1.24
Flash Point, PMCC, °C	233.8

Storage

Mondur MRS 4 isocyanate must be stored in tightly closed containers and protected from contamination with moisture and foreign materials, which can adversely affect processing. PMDI will react slowly with water to form polyureas and liberate CO₂ gas, which may cause sealed containers to expand and rupture. Storage temperatures should be maintained at 18°–30°C (64°–86°F).

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Mondur MRS 4 isocyanate. Before working with this product, you must read and become familiar with the available information on its hazards, proper use, and handling. This cannot be over-emphasized. Information is available in several forms, e.g., material safety data sheets and product labels. Consult your Bayer MaterialScience representative or contact Bayer's Product Safety and Regulatory Affairs Department in Pittsburgh, Pa.

* These items are provided as general information only. They are approximate values and are not considered part of the product specifications.

** Brookfield viscosity method.

Note: The information contained in this bulletin is current as of February 1997. Please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • www.BayerMaterialScienceNAFTA.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Sales Offices

17320 Redhill Avenue, Suite 175, Irvine, CA 92614-5660 • 1-949-833-2351 • Fax: 1-949-752-1306
1000 Route 9 North, Suite 103, Woodbridge, NJ 07095-1200 • 1-732-726-8988 • Fax: 1-732-726-1672
2401 Walton Boulevard, Auburn Hills, MI 48326-1957 • Phone: 1-248-475-7700 • Fax: 1-248-475-7701

