

# MULTRANOL<sup>®</sup> 8116

## *Polyether Polyol*

**CAS No. 9082-00-2**

Product Code: **K8116**

### Description

Multranol 8116 is a 1,400-molecular-weight polypropylene oxide-based triol specially modified with ethylene oxide. It can be used in the production of rigid and flexible foams, adhesives, sealants, specialty elastomers and coatings. As with any product, use of Multranol 8116 polyol in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

### Product Specifications

Property	Value
Hydroxyl Number	115–125 mg KOH/g
Water, Wt. %	≤0.05%
Acid Number	≤0.10 mg KOH/g

### Typical Properties\*

Property	Value
Appearance	Colorless to pale yellow liquid
Specific Gravity at 25°C	1.00
Flash Point, PMCC	>93°C
Bulk Density at 25°C	8.35 lb/gal

### Storage

Multranol 8116 polyol is slightly hygroscopic and may absorb water. Containers should be kept tightly closed and protected from contamination with moisture and foreign materials, which can adversely affect processing.

This polyol can become viscous at low temperatures. For ease of handling, storage temperatures between ambient room temperature and 49°C (120°F) are recommended.

### Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Multranol 8116 polyol. Before working with this product, you must read and become familiar with the available information on its hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets and product labels. Consult your Bayer Material Science representative or contact the Product Safety and Regulatory Affairs Department in Pittsburgh, Pa.

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Note: The information contained in this bulletin is current as of July 2001. Please contact Bayer MaterialScience to determine whether this publication has been revised.

## Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • [www.BayerMaterialScienceNAFTA.com](http://www.BayerMaterialScienceNAFTA.com)

The conditions of your use and applications of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. All information is given without warranty or guarantee, and is subject to change without notice. It is expressly understood and agreed that the customer assumes and hereby expressly releases us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

